

STAINSEAL 916W

Water & Oil Repellent Impregnator

GENERAL DESCRIPTION

AXEL STAINSEAL 916W is a water based silane / siloxane / fluoropolymer mixture, specially formulated for use as an impregnator. It is designed to impart water and oil repellency to easy-care finishes of natural stone or unglazed ceramic and brick tiles, exterior marble, granite stonework, or other surfaces where water and oil repellency is required.

AXEL STAINSEAL 916W is specially blended to give a high water repellency action, reduce staining and efflorescence.

RECOMMENDED USES

- * Concrete
- * Marble
- * Slates
- * Terracotta
- * Brickworks
- * Granites
- * Other Architectural Stones

CHARACTERISTICS & ADVANTAGES

- * Durable, good resistance to U.V. lights
- * Economical, easy to apply, minimizes cleaning costs
- * Prevents staining, promotes easy cleanup
- * High alkaline resistance
- * Acts as a good anti – efflorescence.

COVERAGE

Depending on porosity of substrates, approximate usage is as follows:

- Bricks : 4 to 5 m²/lit
- Stonework : 6 to 8 m²/lit
- Concrete/Plaster : 4 to 6 m²/lit

COLOURS

Colorless

PACKING

5 litre and 20 litre per pail

STORAGE

Store in a dry, cool and shaded place



STAINSEAL 916W

Water & Oil Repellent Impregnator

SURFACE PREPARATIONS

The substrate to be treated must be dry, clean and free from oil, grease and other contaminants. Cement laitance, loose particles, cured membranes, etc. must be removed.

Any cracks, honeycomb or uneven surfaces should be repaired before application.

New concrete structures should be cured for at least 28 days

METHOD OF APPLICATION

- * Apply **AXEL STAINSEAL 916W** evenly with brush, roller, or conventional and airless Spray
- * Apply two or more coats by the chosen method of application, allowing 20-30 minutes between coats.
- * Wipe off the excess material when the treated surface already saturated.
- * Allow coated surfaces to set for at least 24 hours before putting into service.
- * A preliminary test on the surface to be treated is recommended. If a sufficient quantity of **AXEL STAINSEAL 916W** is treated will yield an optimal waterproofing performance.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened or cured material can only be mechanically removed.

TECHNICAL SPECIFICATIONS

No. of components	One
Finishing	Natural (no film formation)
Specific gravity (25°C)	0.95-1.1 kg/l
Dilution	Not required
Flash point	Non flammable
Resistance to water under pressure	1.4 kg/cm ² (20lb/sq. Inch)
Drying time (28°C)	Surface dry : 20-30 minutes Hard dry : 60 minutes (Dependent on temperature and humidity)

SHELF LIFE

12 months from the date of production if stored properly in original, unopened and undamaged sealed packaging in dry conditions.

The above data is provided in good faith and to the best of our knowledge. However, since application and services conditions are beyond our control, we do not accept liability relating to coverage, performance and injury arising from the use of our products based on the data. Further with the constant advancement of technology we reserve the right to modify data without prior notice and we advise that you check with our Axelchem Technical Department at Tel: 603-6276 2118 the validity of these data especially if more than six months have lapsed since issue.